



A LEGACY OF INNOVATION. A FUTURE OF EXCELLENCE.

PRODUCT DATASHEET

UNBLEACHED EUCALYPTUS KRAFT PULP (UEKP)

UNBLEACHED PULP

	Method	Typical Values*
ISO Brightness, %	ISO 2470-1	32 – 42
Kappa Number, mm ² /kg	ISO 302	12 – 18
Viscosity, ml/g	ISO 5351	1000 – 1300
pH (cold aqueous extract)	ISO 6588-1	8.0 – 10.0

	Method	Typical Values*	
Revolutions (PFI mill), #	ISO 5264-2	0	1500
Schopper-Riegler, oSR	ISO 5267-1	20 ± 3	36 ± 7
Bulk, cm ³ /g	ISO 534	1.73 ± 0.08	1.44 ± 0.08
Tensile Index, N.m/g	ISO 1924-2	35.0 ± 8.0	78.0 ± 10.0
Burst Index, kPa.m ² /g	ISO 2758	1.60 ± 0.40	5.30 ± 0.08
Tear Index, mN.m ² /g	ISO 1974	5.30 ± 1.50	10.00 ± 1.00
Air Resistance Gurley, s/100 ml	ISO 5636-5	1.3 ± 0.5	13.00 ± 8.0

*Typical values are based on standard sample testing and show typical pulp quality results, but they do not define the product specification. The values provided hereby can be changed at any time by The Navigator Company.

Learn more at
www.gcell-pulp.com



PACKAGING

Sheets

Basis weight, g/m ²	950-1300
Size (l x w), cm	82x75

Bales

Gross weight, kg	250
Size (l x w x h), cm	82x75x45

Wrapper	1 sheet of Unbleached Kraft Paper (wrapper is free from wet-strength resins and other noxious additives)
---------	--

Marking	Black Ink-Jet Printing
---------	------------------------

Wrapper basis weight, g/m ²	140 ± 5
--	---------

Wires Type	Galvanized
------------	------------

Wires, #	≥2
----------	----

Wires diameter, mm	2.18 ± 0.04
--------------------	-------------

Bales per unit, #	8
-------------------	---

Units

Gross weight, kg	2000
------------------	------

Size (l x w x h), cm	82x150x180
----------------------	------------

Wires Type	Galvanized
------------	------------

Wires, #	≥ 7
----------	-----

Wires diameter, mm	3.0 ± 0.05
--------------------	------------

